

Minimum Slip Resistance

- The slip resistance of the proposed new surface, as measured by a Wet Pendulum test after 500 wear cycles on the Accelerated Wear Test, must be greater than or equal to those outlined below for the proposed location:

Location	Minimum Slip Resistance (after 500 wear cycles)
Customer Areas (max grade 1:20)	BPN=35+
Ramp (max grade 1:14)	BPN=45+
Ramp (max grade 1:8)	BPN=50+